



# Chrome Nitride

Chrome nitride is used to adjust residual nitrogen in superalloys, and for production of medical alloys. Nitrogen content can be adjusted upon request.

Chrome nitride powders are also available for welding applications.

## 01 Standard Specifications

	Al	Fe	Si	O	N	C	S	P	Cr
Max (ppm)	300	2000	800	2000	8-12%	1000	30	20	Balance
Typical (ppm)	100	1000	400	1200		250	20	10	

Other specifications are available upon request

## 02 Size

Briquettes 1.20"x1"x0.6" (30x25x15 mm) - or according to powder specifications

## 03 Packing

Steel drums 500lb / 250 kg

Customs tariff 81122190  
REACH registration no. 05-2118327759-28-0000



## CONTACT

[info@dcx-chrome.com](mailto:info@dcx-chrome.com)

**Head office and plant location**  
**DCX Chrome SAS**  
– Delachaux Group  
68, rue Jean Jaurès  
59770 Marly, France  
Tel +33 3 27 20 07 77

**USA - Delachaux Metal Inc.**  
26 Interstate Drive - P.O. Box 69  
Napoleon, Ohio 43545 - USA  
Phone 631-373-0212

# DCX CHROME

⊕ GROUPE DELACHAUX